NO. 862 P. 3

Attorney Docket No. P68040US1 Application No. 10/674,824

## Amendments to the claims:

This listing of claims replaces all prior versions, and listings, of claims in the application.

## Listing of claims:

- 1 (currently amended): A moisture-curing one-pack urethane adhesive composition comprising
  - a) an isocyanate group-terminated urethane prepolymer prepared by reacting polyols with an excess amount of polyisocyanate compounds (OH/NCO = 1/1.5 to 1/4.0), wherein the polyols are selected from the group consisting of polyether polyols, polyester polyols, polyols containing a main chain consisting of C-C bonds, flame-retardant polyols, phosphorus-containing polyols and halogen-containing polyols, the prepolymer being present in an amount of 20 to 60% by weight.
  - b) a hexamethylene diisocyanate derivative selected from the group consisting of a biuret derivative, and an isocyanurate derivative and a trimethylolpropane derivative, which is present in an amount of 0.5 to 10% by weight,
  - c) a silane coupling agent and/or a polyisocyanate derivative of a silane coupling agent, as an adhesive promoter, which is present in an amount of 0.1 to 5% by weight, and
  - d) (i) 2,2'-dimorpholinodiethyl ether and/or di(2,6-dimethylmorpholinoethyl)ether which is present in an amount of 0.05 to 2.0% by weight, and (ii) at least one tin-based catalyst selected

SEP. 15. 2006 8:32PM JACOBSON HOLMAN PLLC NO. 862 P. 4

Attorney Docket No. P68040US1 . Application No. 10/674,824

from the group consisting of dibutyltin diacetylacetonate, dibutyltin dilaurate, dibutyltin diacetate, dibutyltin dimaleate, dioctyltin dilaurate and tin octanoate, as curing catalysts, which is present in an amount of 0.0001 to 0.5% by weight,

wherein all the amounts are based on the adhesive composition as a whole.

Claims 2-4 (cancelled).

5 (previously presented): The moisture-curing one pack urethane adhesive composition according to claim 1 in which the adhesive promoter is a silane coupling agent and the silane coupling agent

is at least one compound selected from the group consisting of mercaptopropyltrimethoxysilane,

mercaptopropylmethyldimethoxysilane,  $\gamma$ -N-phenylaminopropyltrimethoxysilane and  $\gamma$ -isocy-

anatopropyltrimethoxysilane.

6 (previously presented): The moisture-curing one-pack urethane adhesive composition according

to claim 1 in which the adhesive promoter is a reaction product of a silane coupling agent with

a hexamethylene diisocyanate derivative.

Claim 7 (cancelled).

3